


AMENDMENT OF THE CLAIMS

Claims 23 and 25-27 have been amended. Claim 30 has been added.

This listing of claims will replace all prior versions and listings of claims in the application.

Claims 1-16 (canceled).

17. (Original) An optical waveguide system or a structure or part thereof, comprising a resin composed of at least one polycyanate copolymer, obtainable by copolymerization of at least one difunctional cyanate of formula II:



wherein R^1 to R^4 and R^5 to R^8 are independently from each other hydrogen, optionally substituted C_1 - C_{10} alkyl, C_3 - C_8 -cycloalkyl, C_1 - C_{10} -alkoxy, halogen, phenyl or phenoxy, the alkyl or aryl groups being unfluorinated, partly fluorinated or fully fluorinated, Z is a chemical bond, SO_2 , CF_2CH_2 , CHF, $CH(CH_3)$, isopropylene, hexafluoroisopropylene, n- or iso- C_1 - C_{10} alkylene, O, NR^9 , $N=N$, $CH=CH$, $C(O)O$, $CH=N$, $CH=N-N=CH$, alkyl oxyalkylene having 1 to 8 carbon atoms, S, $Si(CH_3)_2$, and R^9 is hydrogen or C_1 - C_{10} alkyl

with at least one monocyanate of the following formula I:



wherein R is a straight or branched non-aromatic hydrocarbon radical or a non-aromatic hydrocarbon radical comprising a cyclic structure, the radical having the formula $C(R')_2-CFR''_2$ wherein each R' is, independently from the other, hydrogen or fluorine or an optionally substituted alkyl or alkenyl group, and each of R'' may independently be defined as R' or may have an aryl structure.

18. (Original) An optical waveguide system or a structure or part thereof according to claim 17, wherein the substituted alkyl or alkenyl group of R' is fluorinated.

19. (Original) An optical waveguide system or a structure or part thereof according to claim 17, wherein the polycyanate copolymer is obtainable by copolymerization of at least one difunctional cyanate of formula II, at least one monofunctional cyanate of formula I and at least one dicyanate having formula III:



wherein R^{10} is a non-aromatic hydrocarbon group carrying at least one fluorine atom.


20. (Original) An optical waveguide system or a structure or part thereof according to claim 19, wherein R^{10} of formula III is a partly or fully fluorinated alkylene group having 1 to 15 carbon atoms.

21. (Original) An optical waveguide system or a structure or part thereof according to claim 20, wherein the partly or fully fluorinated alkylene group has 3 to 12 carbon atoms.

FINNEGAN
HENDERSON
FARABOW
GARRETT &
DUNNER LLP

1300 I Street, NW
Washington, DC 20005
202.408.4000
Fax 202.408.4400
www.finnegan.com

22. (Original) An optical waveguide system or a structure or part thereof according to claim 19, wherein the polycyanate copolymer is obtainable by copolymerization of at least one difunctional cyanate of formula II, at least one monofunctional cyanate of formula I, optionally at least one dicyanate having formula III, and a monocyanate of formula IV



(IV)

wherein R¹ to R⁵ are defined as in formula II.

23. (Currently Amended) An optical waveguide system or a structure or part thereof according to claim 19, wherein the polycyanate copolymer is obtainable by copolymerization of at least one difunctional cyanate of formula II, at least one monofunctional cyanate of formula I, and at least one brominated monocyanate of formulas I to III, as defined above with the proviso that the **brominated** monocyanates of formula I may be free of fluorine.

24. (Original) An optical waveguide system or a structure or part thereof according to claim 23, wherein the at least one brominated monocyanate is of formula I as defined above with the proviso that the monocyanates of formula I may be free of fluorine.

25. (Currently Amended) An optical waveguide system or a structure or part thereof according to claim 17, wherein the monocyanate of formula I is used in an amount of at least 10 mol% ~~by mol~~ per mol of the polycyanate copolymer.

26. (Currently Amended) An optical waveguide system or a structure or part thereof according to claim 17, wherein the monocyanate of formula I is used in an amount of at least 20 mol% ~~by mol~~ per mol of the polycyanate copolymer.
27. (Currently Amended) An optical waveguide or a structure or part thereof according to claim 17, wherein the polycyanate copolymer has a glass transition temperature of from 100°C to 300°C or a refractive index of about 1.35 to about 1.60 at 1.55µm ~~or a glass transition temperature of from 100°C to 300°C and a refractive index of about 1.35 to about 1.60 at 1.55µm.~~
28. (Original) An optical waveguide system or a structure or part thereof according to any one of claims 17 to 27, wherein the system, structure or part thereof is an optical fibre, a waveguide, a buffer layer, a cladding or a support for any of said structures.
29. (Original) An optical waveguide system comprising a waveguide consisting of a resin as defined in any one of claims 17 to 27, and a buffer or cladding consisting of a resin as defined in any one of claims 17 to 27, but different from the resin of the waveguide, wherein the resin of the waveguide has a greater refractive index than that of the buffer or cladding.
30. (New) An optical waveguide or a structure or part thereof according to claim 17, wherein the polycyanate copolymer has a glass transition temperature of from 100°C to 300°C and a refractive index of about 1.35 to about 1.60 at 1.55µm.